

Typical Properties	Typical Value	Units
Physical Data		
Specific Gravity	1.85	
Water Absorption-.125"	< 2.0	%
Temperature Index	170 \ 338	°C \ °F
Rockwell Hardness	110	M scale
Bond Strength	> 850 \ 386	LBS \ kgs
Flexural Strength-LW-A-.125"	> 40,000 \ 276	PSI \ MPa
Flexural Strength-CW-A-.125"	> 30,000 \ 207	PSI \ MPa
Izod Impact Strength-LW	> 9	ft-lbs/in
Izod Impact Strength-CW	> 7	ft-lbs/in
Compressive Strength-Flatwise	> 50,000 \ 345	PSI \ MPa
Electrical Data		
Dielectric Breakdown-A	> 50	kV